

**ASFALTBETOONSEGUDE LUBATUD SEGAMISTEMPERATUURIDE  
VAHEMIKUD**

Bituumeni mark	Segamistemperatuur °C
50/70	145–175
70/100	140–170
100/150	135–165
160/220	130–160
250/330	125–155
330/430	115–155
500/650	110–150
650/900	110–140
V 1500	40–120
V 3000	50–120
V6000	110–140
PMB 45/80-65 PMB 65/105-65 PMB 75/130-70	Vastavalt sideaine tootja soovitudele lähtudes kasutatava modifikaatori omadustest (oriendruvalt 170–190)