

STABILISEERITUD KIHTIDE TERASTIKULINE KOOSTIS

Segu kasutamise koht		Sõela ava, mm											
		64	32	16	12	8	4	2	1	0,5	0,25	0,125	0,063
		Läbib sõela, % täitematerjali massist											
Alustes TS 32*	Min	100	80	60	52	43	33	24	18	13	10	8	6
	Max	100	100	85	76	63	48	39	31	26	21	18	15
Alustes BS 32*	Min	100	71	51	45	36	26	19	14	11	9	7	6
	Max	100	99	77	71	60	46	36	30	25	21	18	16
Alustes KS 32*	Min	100	80	60	52	43	33	24	18	13	10	8	6
	Max	100	100	85	76	63	48	39	31	26	21	18	16
Katetes TS 16*	Min	100	100	90	80	63	45	32	23	13	10	8	6
	Max	100	100	100	97	85	70	54	42	32	25	18	15
Katetes BS 16*	Min	100	100	90	80	63	45	32	23	16	12	9	6
	Max	100	100	100	97	85	70	54	42	33	27	20	15
Katetes KS 16*	Min	100	100	90	80	63	45	32	23	13	10	8	6
	Max	100	100	100	97	85	70	54	42	32	25	18	15

*Nende tähistega taga olev number tähistab maksimaalset terasuurst.